

Anode Selection Guide



FOR SALT & BRACKISH WATER

This information is a general guide only. When any changes are being made to the cathodic protection system on any vessel, seek Professional advice. Signs of corrosion action may not be related to anodes installed, and may be an indication of an electrically induced corrosion action, or other types of corrosion not prevented by the use of sacrificial anodes. If in doubt, contact a corrosion specialist. When in warranty, always use OEM or manufacturer specified anodes to prevent defecting warranty. Guide is indicative for salt and brackish water applications only.

| | | ANODE TYPE | | | |
|------------------------------------|------------|----------------------------------|--------|-----------|---------|
| | | MADDOX™ | ZINC | ALUMINIUM | |
| RECOMMENDED POTENTIAL VOLTAGE (MV) | 550 - 900 | FIBREGLASS | | | |
| | | Stainless & Bronze (shaft, IPS)* | ● | ● | ● |
| | 950 - 1050 | Aluminium | ● | ● | ● |
| | 550 - 600 | WOOD | | | |
| | | Stainless & Bronze (shaft, IPS)* | ● | ● | ● |
| | 900 - 1050 | Aluminium | ● | ● | ● |
| | 950 - 1050 | ALUMINIUM | | | |
| | | Stainless & Bronze (shaft, IPS)* | ● | ● | ● |
| | 900 - 1100 | Aluminium | ● | ● | ● |
| | 800 - 1050 | STEEL | | | |
| | | Stainless & Bronze (shaft, IPS)* | ● | ● | ● |
| | 900 - 1100 | Aluminium | ● | ● | ● |
| | 550 - 900 | CARBON FIBRE | | | |
| | | Stainless & Bronze (shaft, IPS)* | ● | ● | ● |
| | 900 - 1050 | Aluminium | ● | ● | ● |
| | 550 - 900 | TRIM TABS & SWIM PLATFORM | | | |
| | | Stainless & Bronze (shaft, IPS)* | ● | ● | ● |
| | 900 - 1050 | Aluminium | ● | ● | ● |
| | | | -750MV | -1050MV | -1100MV |

*Fibreglass shaft driven vessels (stainless & bronze) are recommended to achieve cathodic protection no greater than 750mV for coating longevity and best efficiencies.

| WHAT IS? | |
|---|--|
| OVERPROTECTION: <ul style="list-style-type: none"> • Paint blasting and premature coating failure • Excessive anode wear • Marine growth on running gear • Alkaline degradation (wood vessels) | UNDERPROTECTION: <ul style="list-style-type: none"> • Galvanic corrosion • Imbalanced anode wear • Corrosion within engine components • Coating failure |

This material remains the exclusive property of Marine Protection Systems Pty Ltd and must not be reproduced, replicated, copied or used without the expressed consent of Marine Protection Systems Pty Ltd © 2020

| TABLE KEY | |
|-----------|--|
| ● | Ideal cathodic protection |
| ● | Use caution. May cause over-protection or consideration with other anodes installed to ensure similarity to all anodes connected directly or indirectly. |
| ● | Not suitable. Will not protect or will cause significant problems associated with overprotection. |

[f @marineprotectionsystems](https://www.facebook.com/marineprotectionsystems)
[@marineprotectionsystems](https://www.instagram.com/marineprotectionsystems)
info@marineprosystems.com

CORROSION CONTROL THAT WORKS